

Product Data Sheet

SeaCell™MT 1.7 dtex 38 or 60 mm (based on Modal Technology)

**Cellulose fiber with incorporated seaweed (*Ascophyllum nodosum*)
produced according to the modified viscose-process**

Fibre composition in conditioned state (% by weight):

Cellulose	≥ 83 %
Seaweed powder	4 %
Fiber finish	0.3 %
Moisture	12 %
Appearance	light brown

Average textile physical fiber data:

Titer	d'tex	1.7
Cut length	mm	38 / 60
Tenacity dry	cN/tex	≥ 25
Elongation dry	%	11-14
Tenacity wet	cN/tex	≥ 13
Elongation wet	%	11-14
BISFA wet modulus	cN/tex/5%	≥ 4

Cellulose is wood pulp made out of beech tree.

smartfiber AG

Im Weidig 12
07407 Rudolstadt / Deutschland

Tel.: 0049 3672 3494 - 0
Fax: 0049 3672 3494 - 34
E-Mail: mail@smartfiber.de
Internet: www.smartfiber.de

Rudolstadt, December 2016